## **Casting Powder**

No. SMMP020-0

| Other Names   | Mold Powder, Mold Slag, Protective Slag   |  |   |   |  |
|---|---|--|---|---|--|
| Items/Grades  | CP-LC   | СР-НС  | CP-SS   | CP-SiS  | CP-PP  |
| CaO<br>SiO2<br>Al2O3<br>Fe2O3<br>F<br>Na2O  | 33-37<br>34-38<br><=3.5<br><=2.5<br>4-8   | 26-30<br>28-32<br><=6<br><=2.5<br>4-9<br>6-10  | 30-36<br>31-37<br>4-8<br><=2.5<br>4-8<br>5-9  | 31-35<br>30-34<br><=5<br><=2.5<br>5-9<br>6-10   | 26-32<br>26-32<br><=6<br><=2.5<br>5-9  |
| C   | 3-6   | 14-22  | <=5   | <=3   | 18-22  |
| Section (mm) Casting Speed (m/min) Steel Grade Melting Point (°C) Melting Speed (s at 1,250°C) Moisture (%) Viscosity (p s 1,300°C) | (150-160) x (700-1500)<br>0.6-1<br>Common Carbon, Low Alloy<br>1,130+/-30<br>25+/-10<br><=0.5<br>0.25+/-0.05  | 150-230<br>1-2<br>High Carbon, #45 Steel<br>1,100+/-30<br>30+-10<br><=0.5<br>0.2+-0.05 | 150-250<br>0.6-1.5<br>Stainless Steel<br>1,135+/-30<br>25+/-10<br><=0.5<br>0.3+-0.1 | (180-250) x (1,050-1,400)<br>0.9-1.4<br>Silicon Steel<br>1,090+/-30<br>25+-10<br><=0.5<br>0.2+-0.05 | ø150-230<br>1.8-2.4<br>Petroleum Pipe<br>1,130+/-30<br>30+/-10<br><=0.5<br>0.25+/-0.05 |
| Grain Size (mm)   | 0.1-3   | 0.1-3  | 0.1-1   | 0.9-1.4   | 1.8-2.4  |
| Packing   | 10kg in one bag, 800kg in one jumbo bag, 16MT in 1x20'fcl   |  |   |   |  |
| Photos for Reference  |   |  |   |   |  |
| Friendly Reminder   | Casting Powder is a rather complicated material with various grades. The above 5 grades are for reference only. According to section, casting speed, steel grade and caster index, our casting powder factory may decide to use which grade. Our casting powder factory is one of the leading Chinese manufacturers with almost 40 years experience. They have rich practice in flexible product formulation adjustments, stable quality control and aftersales service to meet customers for all steel various and working conditions. |  |   |   |  |

